

Product: NONWOVENS
Composition : Polypropylene

Main fonction

Filtration

Property	Test method	Imperial	Metric
Physical			
Thickness	ASTM-D5729	0.10 in	2.60 mm
Mechanical			
Tensile strength CD	ONGC 148.1 No.7.3	20 lbs	90 N
Tensile strength MD	ONGC 148.1 No.7.3	20 lbs	90 N
Bursting strength	ONGC 4.2 No.11.1	102 psi	700 kPa
Hydraulic			
FOS	ONGC 148.1 No.10	450 - 900 μ m	450 - 900 μ m
Packaging			
Standard Width	ASTM D461.9	137.80 in	3.50 m
Standard Length	ASTM D461.8	55 yd	50 m

All values are MARV except FOS values.

Our quality management system is certified by ISO-9001 standard.

Texel reserves the right to modify existing properties contingent on the evolution of technical knowledge. Each user is invited to verify if this document represents the most recent update. Texel offers no guarantee and assumes no responsibility regarding usage, installation and/or convenience of usage. Texel must be informed of all product defects or product nonconformity prior to installation. Responsibility is limited to replacement of non-compliant or defective product.