

Product: NONWOVENS

Composition : Polypropylene

Main fonction

Drainage

| Property | Test method | Imperial | Metric |
|--|------------------|----------------|----------------|
| Physical | | | |
| Thickness | ASTM-D5199 | 0.28 in | 7.00 mm |
| Hydraulic | | | |
| Transmissivity 1.0 gradient (H) 8kpa | ASTM-D4716 | 8.0 10e-5 m2/s | 8.0 10e-5 m2/s |
| Transmissivity 1.0 gradient (H) 20kpa | ASTM-D4716 | 6.5 10e-5 m2/s | 6.5 10e-5 m2/s |
| Transmissivity 1.0 gradient (H) 50kpa | ASTM-D4716 | 3.0 10e-5 m2/s | 3.0 10e-5 m2/s |
| Transmissivity 1.0 gradient (H) 150kpa | ASTM-D4716 | 0.9 10e-5 m2/s | 0.9 10e-5 m2/s |
| Water penetration resistance | ONGC 4.2 No.26.3 | 0.0 - 0.8 in | 0.0 - 2.0 cm |
| Packaging | | | |
| Standard Width | ASTM D461.9 | 33.46 in | 0.85 m |
| Standard Length | ASTM D461.8 | 33 yd | 30 m |

All values are MARV except FOS values.

Our quality management system is certified by ISO-9001 standard.

Texel reserves the right to modify existing properties contingent on the evolution of technical knowledge. Each user is invited to verify if this document represents the most recent update. Texel offers no guarantee and assumes no responsibility regarding usage, installation and/or convenience of usage. Texel must be informed of all product defects or product nonconformity prior to installation. Responsibility is limited to replacement of non-compliant or defective product.